TECHNICAL DATA

REGUPOL EVERROLL CROSSTILE 30 mm

Properties	Standard	Result
Material		Components made of synthetic rubber (SBR & EPDM), PUR binder
Thickness		30 mm
Dimensions		1,000 x 500 mm, dummy joint at 500 mm
Weight		approx. 24.0 kg/m²
Force reduction	based on EN 14904 / EN 14808	approx. 58 %
Impact resistance	based on EN 14904 / EN 1517	> 21 Nm
Fire class rating	EN 13501-1:2010-01 / EN 9239-1:2010-11	E_{fl}
Slip resistance	DIN 51130 (02.2014) and ASR A1.5/1.2	R10
Colour fastness	ISO 105 – B02:2002	Blue scale: level 5 Grey scale: level 4
Light reflectance value	EN 13745:2004	3.2 to 5.5 %
Residual indentation	based on DIN EN ISO 24343-1:2012-04	approx. 0.50 mm
Tensile strength	based on DIN EN ISO 1798	approx. 1.05 N/mm²
Elongation at break	based on DIN EN ISO 1798	approx. 72 %
Hardness	based on DIN EN ISO 53505	approx. 40 Shore A
Temperature resistance	In-house testing	-40 to +90 °C
Salt water resistance	based on DIN EN ISO 175	resistant
Vertical standard deformation	based on EN 14904	approx. 2.68 mm
Maximum fall height	based on EN 1177	approx. 1.05 m
CERTIFIED cradle to cradle BRONZE	Cradle to Cradle Certified® is a registered trademark of the Cradle to Cradle Products Innovation Institute.	**REGUPOL everroll crosstile** is Cradle to Cradle Certified® at the Bronze level.

Wherever direct, prolonged or repeated skin contact can be expected, the requirements for a Consumer Product currently valid within the EU must be met. Where this is not expected, your choice can be made from the entire decor portfolio. Those product fulfilling the requirements of a "Consumer Product", are explicitly marked as such. Should any questions arise that need clarification, contact your sales representative at our company directly or write to us using the contact form on our website **www.regupol.com**.

We reserve the right to make alterations to the technical data. All information is subject to fluctuation tolerances of ± 10 %. To verify the accuracy of the contents, please refer to the information on our website **www.regupol.com**.