

REGUFOAM Vibration Isolation

REGUFOAM vibration is an elastic polyurethane foam designed for optimal vibration isolation. It is available in twelve different densities and various thicknesses, now including thinner options, offering even more flexibility to suit diverse needs.

REGUFOAM vibration 990plus

Load range up to 2.5 N/mm². Depending on load and material thickness, natural frequencies of 8 Hz can be achieved.

Product Characteristics

Continuous static load

2.5 N/mm²

Continuous and variable loads/operating load range

0 to 3.5 N/mm²

Peak loads (rare, short-term loads)

up to 8.0 N/mm²

Sheets

Thickness: 12.5 and 25 mm are standard, and regularly available off the shelf. Special thicknesses on request

Length: 1500 mm, special lengths available on request




Width: 1000 mm

Strips or pads

On request: Die-cutting, water-jet cutting, self-adhesive versions possible

On request we can tailor to your needs and produce 75, 50, 37.5, 25, 12.5, 6 mm all the way down to 2 mm thicknesses.

Technical Specifications



Influence of Amplitude

In order to get information of changes in mechanical loss or dynamic stiffness due to changes in amplitudes please ask technical staff of **VIBRATEC**.

REGUFOAM vibration 990plus

Physical property	Norm	Result	Comment
Static modulus of elasticity	Based on EN 826	20.0 - 78.0 N/mm ²	Tangential modulus, see figure "modulus of elasticity"
Dynamic modulus of elasticity	Based on DIN 53513	41.0 160.0 N/mm ²	Depending on frequency, load and thickness, see figure "dynamic stiffness"
Mechanical loss factor	DIN 53513	0.09	Load-, amplitude- and frequency-dependent
Compression set	Based on DIN EN ISO 1856	8.6 %	Measured 30 minutes after decompression with 50 % deformation / 23 °C after 72 hrs
Tensile strength	Based on DIN EN ISO 1798	6.9 N/mm ²	
Elongation at break	Based on DIN EN ISO 1798	190%	
Tear resistance	Based on DIN ISO 34-1	34.5 N/mm	
Fire behaviour	DIN 4102	B2	
	DIN EN 13501-1	E	
Sliding friction	REGUPOL-laboratory	0.5	Steel (dry)
	REGUPOL-laboratory	0.6	Concrete (dry)
Compression hardness	Based on DIN EN ISO 3386-2	3640 kPa	Compressive stress at 25 % deformation test specimen h = 25 mm
Rebound elasticity	Based on DIN EN ISO 8307	55%	dependent on thickness, test specimen h = 25 mm
Force reduction	DIN EN 14904	20%	dependent on thickness, test specimen h = 25 mm



Contact information

Sweden	Norway	Denmark	Estonia	Finland	India
+46 176207880 info@vibratec.se	+47 33070750 info@vibratec.no	+45 49132244 info@vibratec.dk	+372 56627990 info@vibratec.ee	+35 8402589117 palvelu@3di.fi	+91 7755996308 rc@vibratec.in

 vibratec.org/linkedin
 vibratec.org/youtube
 vibratec.org/vimeo